



LIKER LSW

FAT LIQUORS
CHEMICAL COMPOSITION
SULPHORATENATURAL AND SYNTHETIC OIL

CHARACTERISTICS

Properties :	yellow dense liquid
Active substance :	20 – 25% about
pH in solution at 10 % :	7 – 8
Ionic Charge :	anionic
Compatibility :	anionic and not anionic
Biodegradability :	easily biodegradable Directive CEE/67/548

PROPERTIES

The fat-liquoring agent used should be measured out and **LIKER LSW** added with stirring. Water at 60°C should then be stirred into the mixture : it is used alone or combined with suitable **LIKER** products during pickle or mineral tanning.

LIKER LSW gives a better distribution of the fat liquor and an improved stones. In addition to this good penetration gives better physical proprieties and the tear or tensile-strength can be positively influenced.

APPLICATION

Fat-liquoring in the tanning upholstery nappa: weight)	1,5% LIKER LSW (% based on pelt
Re-tanning:	2% LIKER LSW
Wetting back garment or upholstery nappa, crusted : weight)	2 – 3 % LIKER LSW (% based on dry

DATA AND NEWS HAVE INDICATIVE VALUES